

CONTEXT

Rectified Glazed Gres Porcelain

KREM



GRAFFITI

DETAIL



GRAFFITI



DARK GREY

4

PEI

V2

Shades

>6

Mohs



ColdRes

RET

Rectified

SIZE & PACKING INFO Pcs./Ctn. m²/Ctn. Ctn./Pallet kg/Ctn.

30 x 30cm	8	1,44	40	30	Other cut-downs available on request.
60 x 60cm	4	1,44	40	30	
60 x 120cm	2	1,44	40	30	

Coefficient of Friction test results exceed A.D.A recommendations ASTM C-1028 >0.60 wet DCOF >0.42

PRODUCT DESCRIPTION

Rectified 60x60 & 60x120cm Floor Tile
Available in Matt Mould and upon request, R11 anti-slip finishes.
4 faces 60x120cm

CONTEXT

DARK GREY

4 faces 60x120cm

KREM



CONTEXT

GRAFFITI

4 faces 60x120cm

KREM



CONTEXT PRODUCT SPECIFICATION

GLAZED GRES PORCELAIN FLOOR TILE

Pressed Ceramic Tiles International Norm

ISO 13006-10545/98

GROUP: B1b

KREM

No.	Icon	Test item	Unit	Requirements of Standard	Test result	Result	
1		Dimensional variation	(%)	length of side	0.6	< 0.6	Qualified
2		Side straightness	(%)	± 0.5		< 0.5	Qualified
3		Squareness	(%)	± 0.5		< 0.5	Qualified
4		Surface flatness	(%)	Center curvature degree	± 0.5	< 0.5	Qualified
				Warping degree	± 0.5	< 0.5	Qualified
				Side curvature degree	± 0.5	< 0.5	Qualified
5		Surface quality	—	Sighting vertically at a distance of 0.8 meter away from the tile no defect on surface is observed in at least 95% of the tile	conformed	Qualified	
6		Water absorption	(%)	Average value ≤ 3 individual ≤ 3.3	< 3 < 3	Qualified	
7		Breaking strength	N	When thickness ≥ 7.5mm the Average value ≥ 700	>700	Qualified	
8		Rupture modulus	Mpa	Average value ≥ 30 individual ≥ 27	> 30 > 30	Qualified	
9		Abrasion resistance	revs	> 1500	> 1700	Qualified Class 3	
10		Scratch resistance	MOH	—	> 6	Qualified	
11		Frost resistance	—	No cracking after test	conformed	Qualified	
12		Resistance to acids & alkalis	—	not less than grade GB	Grade GA	Qualified	
13		Chemical resistance	—	not less than grade GB	Grade GA	Qualified	
15		Slip resistance	R	Ramp slip rating test	R11	Exterior	
			DCoF	DCoF: 0.42	>0.42	Matt/Exterior	