

ROYAL CALACUTTA

Rectified Glazed Floor Tile



ROYAL CALACUTTA



ACTUAL SIZE DETAIL



Royal Calacutta

>6

Mohs

V3

Shades



ColdRes

RET

Rectified

SIZE & PACKING INFO	Pcs./Ctn.	m ² /Ctn.	Ctn./Pallet	kg/Ctn.
30 x 60cm	8	1,44	40	30
60 x 60cm	4	1,44	40	30

Coefficient of Friction test results exceed A.D.A recommendations ASTM C-1028 >0.60 wet DCOF >0.42

PRODUCT DESCRIPTION Rectified Glazed Floor Tile 60 x 60
Polished finish.
5 different faces of 60x60cm.

ROYAL CALACUTTA

5 60x60cm faces 3 60x120cm faces



ROYAL CALACUTTA
5 60x60cm faces 3 60x120cm faces

KREM



ROYAL CALACUTTA PRODUCT SPECIFICATION



GLAZED FLOOR TILE

Pressed Ceramic Tiles International Norms

ISO 13006–10545/98

GROUP: B1

No.	Icon	Test item	Unit	Requirements of Standard	Specification	Requirement	
1		Dimensional variation	(%)	length of side	±0.6	< 0.6	Qualified
2		Side straightness	(%)	± 0.5		< 0.5	Qualified
3		Squareness	(%)	± 0.6		< 0.6	Qualified
4		Surface flatness	(%)	Center curvature degree	± 0.5	< 0.5	Qualified
				Warping degree	± 0.5	< 0.5	Qualified
				Side curvature degree	± 0.5	< 0.5	Qualified
5		Surface quality	—	Sighting vertically at a distance of 0.8 meter away from the tile no defect on surface is observed in at least 95% of the tile	conformed	Qualified	
6		Breaking strength	N	When thickness ≥ 7.5mm the Average value ≥ 1100	> 1100	Qualified	
7		Rupture modulus	Mpa	Average value ≥ 30 individual ≥ 27	> 30 > 30	Qualified	
8		Abrasion resistance	Revs	1500	> 1500	Qualified	
9		Hardness	MOHS	Mohs Scale	> 6	Qualified	
10		Frost resistance	—	No cracking after test	conformed	Qualified	
11		Resistance to acids & alkalis	—	not less than grade GB	Grade GA	Qualified	
12		Chemical resistance	—	not less than grade GB	Grade GA	Qualified	