NOVA

Rectified Glazed Floor Tile











>6
Mohs







SIZE & PACKING INFO	Pcs./Ctn.	m ² /Ctn.	Ctn./Pallet	kg/Ctn.
30×60 cm	8	1,44	40	28
60 x 60cm	4	1,44	40	29
60 x 120cm	2	1.44	40	35

Coefficient of Friction test results exceed A.D.A recommendations ASTM C-1028 > 0.60 wet DCOF > 0.42





















NOVA PRODUCT SPECIFICATION

GLAZED FLOOR TILE

Pressed Ceramic Tiles International Norms

ISO 13006-10545/98

GROUP: B1



No.	Icon	Test item	Unit	Requirements of Standard		Specifica- tion	Require- ment
1	+	Dimensional variation	(%)	length of side	±0.6	< 0.6	Qualified
2	←	Side straightness	(%)	± 0.5		< 0.5	Qualified
3		Squareness	(%)	± 0.6		< 0.6	Qualified
				Center curvature degree	± 0.5	< 0.5	Qualified
4	<u>+ +</u>	Surface flatness	(%)	Warping degree	± 0.5	< 0.5	Qualified
				Side curvature degree	± 0.5	< 0.5	Qualified
5	Q	Surface quality		Sighting vertically at a distance of 0.8 meter away from the tile no defect on surface is observed in at least 95% of the tile		conformed	Qualified
6		Breaking strength	N	When thickness ≥ 7.5mm the Average value ≥ 1100		> 1100	Qualified
7	[Rupture modulus	Мра	Average value ≥ 30 individual ≥ 27		> 30 > 30	Qualified
8		Abrasion resistance	Revs	1500		> 1500	Qualified
9	***	Hardness	MOHS	Mohs Scale		> 6	Qualified
10	**	Frost resistance		No cracking after test		conformed	Qualified
11	1	Resistance to acids & alkalis		not less than grade GB		Grade GA	Qualified
12		Chemical resistance		not less than grade GB		Grade GA	Qualified
13	معک	Olin magists	R	Ramp slip rating test		R11	Exterior
	/_	Slip resistance		DCoF: 0.42		>0.42	Matt/ Exterior