

# OCEANIC


Rectified Matt Glazed Floor Tile



Grigio



Ivory



Beige (Dark)

- V2**  
Shades
-   
ColdRes
- RET**  
Rectified

<b>SIZE &amp; PACKING INFO</b>	Pcs./Ctn.	m <sup>2</sup> /Ctn.	Ctn./Pallet	kg/Ctn.
30 x 60cm	8	1,44	40	28
60 x 60cm	4	1,44	40	29
60 x 120cm	2	1,44	40	35

Coefficient of Friction test results exceed A.D.A recommendations ASTM C-1028 >0.60 wet DCOF >0.42

**PRODUCT DESCRIPTION** Rectified 30 x 60 & 60 x 60 & 60 x 120 cm Glazed Floor Tile  
Available in Polished and Matt finish or an Exterior finish on request.  
6 different faces. Also available in polished finish.



**OCEANIC**  
GRIGIO  
6 faces

**KREM**





**OCEANIC**  
IVORY & BEIGE (DARK)  
6 faces each

**KREM**



# OCEANIC PRODUCT SPECIFICATION

## GLAZED FLOOR TILE

Pressed Ceramic Tiles International Norms

ISO 13006-10545/98

GROUP: B1



No.	Icon	Test item	Unit	Requirements of Standard	Specification	Requirement	
1		Dimensional variation	(%)	length of side	±0.6	< 0.6	Qualified
2		Side straightness	(%)	± 0.5		< 0.5	Qualified
3		Squareness	(%)	± 0.6		< 0.6	Qualified
4		Surface flatness	(%)	Center curvature degree	± 0.5	< 0.5	Qualified
				Warping degree	± 0.5	< 0.5	Qualified
				Side curvature degree	± 0.5	< 0.5	Qualified
5		Surface quality	—	Sighting vertically at a distance of 0.8 meter away from the tile no defect on surface is observed in at least 95% of the tile	conformed	Qualified	
6		Breaking strength	N	When thickness ≥ 7.5mm the Average value ≥ 1100	> 1100	Qualified	
7		Rupture modulus	Mpa	Average value ≥ 30 individual ≥ 27	> 30 > 30	Qualified	
8		Abrasion resistance	Revs	1500	> 1500	Qualified	
9		Frost resistance	—	No cracking after test	conformed	Qualified	
10		Resistance to acids & alkalis	—	not less than grade GB	Grade GA	Qualified	
11		Chemical resistance	—	not less than grade GB	Grade GA	Qualified	
12		Slip resistance	R	Ramp slip rating test	R11	Exterior	
			DCoF	DCoF: 0.42	>0.42	Matt/ Exterior	