VEGA

Rectified Glazed Floor Tile



















SIZE & PACKING INFO	Pcs./Ctn.	m^2/Ctn .	Ctn./Pallet	kg/Ctn.
30×60 cm	8	1,44	40	30
60 x 60cm	4	1,44	40	30
60 x 120cm	2	1,44	40	30

Coefficient of Friction test results exceed A.D.A recommendations ASTM C-1028 >0.60 wet DCOF >0.42











VEGA PRODUCT SPECIFICATION

GLAZED FLOOR TILE
Pressed Ceramic Tiles International Norm
ISO 13006-10545/98
GROUP: B1



Specifica-Require-No. **Icon** Test item Unit **Requirements of Standard** tion ment Dimensional 1 (%) length of side ±0.6 < 0.6 Qualified variation 2 Side straightness < 0.5 Qualified (%) ± 0.5 3 Squareness (%) < 0.6 Qualified ± 0.6 Center curvature ± 0.5 < 0.5 Qualified degree 4 Surface flatness (%)Warping degree < 0.5 Qualified ± 0.5 Side curvature < 0.5 Qualified ± 0.5 degree Sighting vertically at a distance of 0.8 meter away from the tile 5 Surface quality conformed Qualified no defect on surface is observed in at least 95% of the tile When thickness ≥ 7.5mm 6 Breaking strength Ν > 1100 Qualified the Average value ≥ 1100 Average value ≥ 30 > 30 7 Rupture modulus Мра Qualified individual ≥ 27 > 30 Revs Abrasion resistance 1500 > 1500 Qualified 8 MOHS Mohs Scale Qualified 9 Hardness > 6 10 Qualified Frost resistance No cracking after test conformed Resistance to 11 not less than grade GB Grade GA Qualified acids & alkalis 12 Chemical resistance not less than grade GB Grade GA Qualified Exterior R Ramp slip rating test R11 13 Slip resistance Matt/ **DCoF** >0.42 DCoF: 0.42 Exterior